

# SSPC: The Society for Protective Coatings

## SURFACE PREPARATION SPECIFICATION NO. 2

### Hand Tool Cleaning

#### 1. Scope

1.1 This standard covers the requirements for hand tool cleaning steel surfaces.

#### 2. Definitions

2.1 Hand tool cleaning is a method of preparing steel surfaces by the use of non-power hand tools.

2.2 Hand tool cleaning removes all loose mill scale, loose rust, loose paint, and other loose detrimental foreign matter. It is not intended that adherent mill scale, rust, and paint be removed by this process. Mill scale, rust, and paint are considered adherent if they cannot be removed by lifting with a dull putty knife.

2.3 SSPC-VIS 3 or other visual standard of surface preparation agreed upon by the contracting parties may be used to further define the surface (see Note 8.1).

#### 3. Referenced Standards

3.1 The latest issue, revision, or amendment of the referenced standards in effect on the date of invitation to bid shall govern, unless otherwise specified. Standards marked with an asterisk (\*) are referenced only in the Notes, which are not requirements of this standard.

3.2 If there is a conflict between the requirements of any of the cited reference standards and this standard, the requirements of this standard shall prevail.

##### 3.3 SSPC SPECIFICATIONS:

SP 1	Solvent Cleaning
*SP 3	Power Tool Cleaning
*SP 11	Power Tool Cleaning to Bare Metal
*SP 15	Commercial Grade Power Tool Cleaning
VIS 3	Guide and Reference Photographs for Steel Surfaces Prepared by for Power- and Hand-Tool Cleaning

##### 3.4 INTERNATIONAL ORGANIZATION FOR STANDARDIZATION (ISO):

* 8501-1	Preparation of steel substrates before application of paints and related products: Visual assessment of surface cleanliness—Part I.
----------	---

#### 4. Surface Preparation Before and After Hand Tool Cleaning

4.1 Before hand tool cleaning, visible deposits of oil, grease, or other materials that may interfere with coating adhesion shall be removed in accordance with SSPC-SP 1 or other agreed-upon methods. Nonvisible surface contaminants such as soluble salts shall be treated to the extent specified by the procurement documents [project specifications] (see Note 8.2).

4.2 After hand tool cleaning and prior to painting, reclean the surface if it does not conform to this standard.

4.3 After hand tool cleaning and prior to painting, remove dirt, dust, or similar contaminants from the surface. Acceptable methods include brushing, blow off with clean, dry air, or vacuum cleaning.

#### 5. Methods of Hand Tool Cleaning

5.1 Use impact hand tools to remove stratified rust (rust scale).

5.2 Use impact hand tools to remove all weld slag.

5.3 Use hand wire brushing, hand abrading, hand scraping, or other similar non-impact methods to remove all loose mill scale, all loose or non-adherent rust, and all loose paint.

5.4 Regardless of the method used for cleaning, if specified in the procurement documents, feather the edges of remaining old paint so that the repainted surface can have a reasonably smooth appearance.

5.5 If approved by the owner, use power tools or blast cleaning as a substitute cleaning method for this standard.

## 6. Inspection

**6.1** Unless otherwise specified in the procurement documents, the contractor or material supplier is responsible for quality control to assure that the requirements of this document are met. Work and materials supplied under this standard are also subject to inspection by the purchaser or an authorized representative. Materials and work areas shall be accessible to the inspector.

**6.2** Conditions not complying with this standard shall be corrected. In the case of a dispute, an arbitration or settlement procedure established in the procurement documents (project specification) shall be followed. If no arbitration or settlement procedure is established, then a procedure mutually agreeable to purchaser and material supplier (or contractor) shall be used.

## 7. Disclaimer

**7.1** While every precaution is taken to ensure that all information furnished in SSPC standards and specifications is as accurate, complete, and useful as possible, SSPC cannot assume responsibility nor incur any obligation resulting from the use of any materials, coatings, or methods specified herein, or of the specification or standard itself.

**7.2** This standard does not attempt to address problems concerning safety associated with its use. The user of this standard, as well as the user of all products or practices described

herein, is responsible for instituting appropriate health and safety practices and for ensuring compliance with all governmental regulations.

## 8. Notes

Notes are not requirements of this standard.

**8.1** Note that the use of visual standards in conjunction with this standard is required only when they are specified in the procurement documents (project specification) covering the work. It is recommended, however, that the use of visual standards be made mandatory in the procurement documents.

SSPC-VIS 3 provides a suitable comparative visual standard for SSPC-SP 2, SSPC-SP 3, SSPC-SP 11, and SSPC-SP 15. ISO 8501-1 may also serve as a visual standard.

**8.2** The SSPC Surface Preparation Commentary (SSPC-SP COM) contains additional information and data relevant to this specification. The Commentary is non-mandatory and is not part of this specification. The table below lists the subjects discussed relevant to hand tool cleaning and the appropriate Commentary Section.

<b>Subject</b>	<b>Commentary Section</b>
Film Thickness .....	10
Maintenance Painting.....	4.2
Rust, Stratified Rust, Pack Rust, and Rust Scale .....	4.3.1
Visual Standards .....	11
Weld Spatter.....	4.4.1

# SSPC: The Society for Protective Coatings

## SURFACE PREPARATION SPECIFICATION NO. 3

### Power Tool Cleaning

#### 1. Scope

1.1 This standard covers the requirements for power tool cleaning of steel surfaces.

#### 2. Definition

2.1 Power tool cleaning is a method of preparing steel surfaces by the use of power assisted hand tools.

2.2 Power tool cleaning removes all loose mill scale, loose rust, loose paint, and other loose detrimental foreign matter. It is not intended that adherent mill scale, rust, and paint be removed by this process. Mill scale, rust, and paint are considered adherent if they cannot be removed by lifting with a dull putty knife.

2.3 SSPC-VIS 3 or other visual standard of surface preparation agreed upon by the contracting parties may be used to further define the surface (see Note 8.1).

#### 3. Referenced Standards

3.1 The latest issue, revision, or amendment of the referenced standards in effect on the date of invitation to bid shall govern, unless otherwise specified. Standards marked with an asterisk (\*) are referenced only in the Notes, which are not requirements of this standard.

3.2 If there is a conflict between the requirements of any of the cited reference standards and this standard, the requirements of this standard shall prevail.

##### 3.3 SSPC STANDARDS:

SP 1	Solvent Cleaning
*SP 2	Hand Tool Cleaning
*SP 11	Power Tool Cleaning to Bare Metal
*SP 15	Commercial Grade Power Tool Cleaning
VIS 3	Guide and Reference Photographs for Steel Surfaces Prepared by Hand and Power Tool Cleaning

##### 3.4 INTERNATIONAL ORGANIZATION FOR STANDARDIZATION (ISO):

*8501-1	Preparation of steel substrates before application of paints and related products: visual assessment of surface cleanliness, Part I
---------	---

#### 4. Surface Preparation Before and After Power Tool Cleaning

4.1 Before power tool cleaning, visible deposits of oil, grease, or other materials that may interfere with coating adhesion shall be removed in accordance with SSPC-SP 1 or other agreed-upon methods. Nonvisible surface contaminants such as soluble salts shall be treated to the extent specified by the procurement documents [project specifications] (see Note 8.2).

4.2 After power tool cleaning and prior to painting, reclean the surface if it does not conform to this standard.

4.3 After power tool cleaning and prior to painting, remove dirt, dust, or similar contaminants from the surface. Acceptable methods include brushing, blow off with clean, dry air, or vacuum cleaning.

#### 5. Methods of Power Tool Cleaning

5.1 Use rotary or impact power tools to remove stratified rust (rust scale).

5.2 Use rotary or impact power tools to remove all weld slag.

5.3 Use power wire brushing, power abrading, power impact, or other power rotary tools to remove all loose mill scale, all loose or non-adherent rust, and all loose paint. Do not burnish the surface.

5.4 Operate power tools in a manner that prevents the formation of burrs, sharp ridges, and sharp cuts.

5.5 Regardless of the method used for cleaning, if specified in the procurement documents, feather the edges of remaining old paint so that the repainted surface can have a reasonably smooth appearance.

5.6 If approved by the owner, use blast cleaning as a substitute cleaning method for this standard.

## 6. Inspection

6.1 Unless otherwise specified in the procurement documents, the contractor or material supplier is responsible for timely quality control to assure that the requirements of this document are met. Work and materials supplied under this standard are also subject to inspection by the purchaser or an authorized representative. Materials and work areas shall be accessible to the inspector.

6.2 Conditions not complying with this standard shall be corrected. In the case of a dispute, an arbitration or settlement procedure established in the procurement documents (project specification) shall be followed. If no arbitration or settlement procedure is established, then a procedure mutually agreeable to purchaser and material supplier (or contractor) shall be used.

## 7. Disclaimer

7.1 While every precaution is taken to ensure that all information furnished in SSPC standards and specifications is as accurate, complete, and useful as possible, SSPC cannot assume responsibility nor incur any obligation resulting from the use of any materials, coatings, or methods specified herein, or of the specification or standard itself.

7.2 This standard does not attempt to address problems concerning safety associated with its use. The user of this standard, as well as the user of all products or practices described

herein, is responsible for instituting appropriate health and safety practices and for ensuring compliance with all governmental regulations.

## 8. Notes

Notes are not requirements of this standard.

8.1 Note that the use of visual standards in conjunction with this standard is required only when they are specified in the procurement documents (project specification) covering the work. It is recommended, however, that the use of visual standards be made mandatory in the procurement documents.

SSPC-VIS 3 provides a suitable comparative visual standard for SSPC-SP 2, SSPC-SP 3, SSPC-SP 11, and SSPC-SP 15. ISO 8501-1 may also serve as a visual standard.

8.2 The Surface Preparation Commentary, SSPC-SP COM, contains additional information and data relevant to this specification. The Commentary is non-mandatory and is not a part of this specification. The table below lists the subjects discussed relevant to power tool cleaning and the appropriate Commentary Section.

<b>Subject</b>	<b>Commentary Section</b>
Film Thickness .....	10
Rust Back .....	4.5
Rust, Stratified Rust, Pack	
Rust, and Rust Scale .....	4.3.1
Visual Standards .....	11
Weld Spatter.....	4.4.1



# Interplus 356

## Surface tolerant epoxy

Interplus® 356 is a low VOC, two component, internally flexibilised, high build, low temperature curing epoxy primer. Formulated for surface tolerance to allow application over wet abrasive and ultra high pressure water blasted substrates where dry abrasive blasting is not possible. Interplus® 356 contains lamellar aluminium and micaceous iron oxide pigmentation for improved corrosion resistance.

- High solids, low VOC maintenance epoxy
- Perfect for spray, brush and roller application
- Designed for low temperature cure (down to  $-5^{\circ}\text{C}$  [ $41^{\circ}\text{F}$ ])
- Suitable for rapid overcoating
- Compatible with a wide range of primers, intermediates and topcoats



# Interplus 356 is a high performance maintenance coating for use on a wide variety of surfaces including hand or power tool cleaned rusty steel



## Typical structures

Interplus® 356 is particularly useful in the maintenance of offshore structures and other aggressive environments such as refineries, chemical plants, coastal structures, pulp and paper mills and bridges.



## Intended applications

As a touch-up brush applied primer for hand or power tool cleaned steel, where the fast curing properties allow both cure at low temperatures, and rapid overcoating, thus extending the maintenance painting window and reducing downtime.

## Test data

TEST METHOD	REFERENCE	SPECIFICATION DETAILS	TYPICAL RESULT
Condensation	ISO6270 - "Resistance to continuous condensation @ 35°C (95°F)"	1 x 125µm (5 mils) dft applied directly to Sa2.5 blasted steel (topcoated with Interthane 870)	No film defects following 3000 hours exposure
Cyclic corrosion	Norsok M-501 Revision 2 "Norsok Cyclic Test"	1 x 300µm (11.8 mils) dft applied directly over UHP HB2.5 M-H prepared steel (topcoated with Interfine 629HS)	No blistering, rusting, cracking etc and typically <5mm ( <sup>1/64"</sup> ) rust creep at scribe following 4200hrs exposure
Salt spray	ISO 7253 "Resistance to neutral salt spray (fog) @ 35°C (95°F)"	1 x 250µm (9.8 mils) dft applied directly to Sa2.5 blasted steel (topcoated with Interfine 629HS)	No blistering, rusting, cracking etc and typically <5mm ( <sup>1/64"</sup> ) rust creep at scribe following 6000hrs exposure
Adhesion and immersion	ISO 4624 - "Pull-off test for adhesion" using portable adhesion testers.	1 x 200µm (7.8 mils) dft applied directly to Sa2.5 blasted steel	Not less than 5MPa (725psi) when using a PAT Model GM01 hydraulic adhesion tester on 5mm ( <sup>1/64"</sup> ) thick steel

The above performance data has been compiled based on present experience of in-service product performance and upon performance data obtained under laboratory test conditions. Actual performance of the product will depend upon the conditions in which the product is used.

[www.international-pc.com](http://www.international-pc.com)  
[pc.communication@akzonobel.com](mailto:pc.communication@akzonobel.com)

✕ and **International** and all product names mentioned in this publication are trademarks of, or licensed to, Akzo Nobel. © Akzo Nobel 2014.

International Paint has used its best endeavours to ensure that the information contained in this publication is correct at the time of printing. Please contact your local International Paint representative if you have any questions.

Unless otherwise agreed by us in writing, any contract to purchase products referred to in this brochure and any advice which we give in connection with the supply of products are subject to our standard conditions of sale.

## Technical information

Colour	Aluminium grey		
Volume solids	70%		
Film thickness	75-125µm (3-5 mils) dry		
Mix ratio	3:1 by volume		
Temperature	Touch Dry	Hard Dry	Min Recoat
5°C (41°F)	8 hours	18 hours	10 hours
15°C (59°F)	2 hours	10 hours	6 hours
25°C (77°F)	90 minutes	6 hours	4 hours
40°C (104°F)	45 minutes	3 hours	2 hours
VOC's	305 g/l UK PG6/23 (92), Appendix 3 2.55 lb/gal (305 g/l) US EPA24		

**PRODUCT DESCRIPTION**

A low VOC, two component, internally flexibilized, high build, low temperature curing (down to 23°F, -5°C), surface tolerant epoxy primer. Metallic pigmented, with aluminium and lamellar micaceous iron oxide, for increased corrosion resistance.

**INTENDED USES**

A high performance maintenance coating for use on a wide variety of surfaces including hand or power tool cleaned rusty steel.

Specifically designed for use at low temperatures or where rapid overcoating is essential.

Ideal for use in conjunction with wet abrasive blasting and ultra high pressure water blasting.

Interplus 356 is particularly useful in the maintenance of offshore structures and other aggressive environments such as refineries, chemical plants, coastal structures, pulp and paper mills and bridges when dry abrasive blasting is not possible.

**PRACTICAL INFORMATION FOR INTERPLUS 356**

<b>Color</b>	Aluminum Gray
<b>Gloss Level</b>	Matte
<b>Volume Solids</b>	70%
<b>Typical Thickness</b>	3-5 mils (75-125 microns) dry equivalent to 4.3-7.2 mils (107-179 microns) wet
<b>Theoretical Coverage</b>	225 sq.ft/US gallon at 5 mils d.f.t and stated volume solids 5.60 m <sup>2</sup> /liter at 125 microns d.f.t and stated volume solids
<b>Practical Coverage</b>	Allow appropriate loss factors
<b>Method of Application</b>	Airless Spray, Air Spray - blasted steel Brush, Roller - hand or power tool prepared steel

**Drying Time**

Temperature	Touch Dry	Hard Dry	Overcoating Interval with recommended topcoats	
			Minimum	Maximum
41°F (5°C)	8 hours	18 hours	10 hours	Extended <sup>1</sup>
59°F (15°C)	2 hours	10 hours	6 hours	Extended <sup>1</sup>
77°F (25°C)	90 minutes	6 hours	4 hours	Extended <sup>1</sup>
104°F (40°C)	45 minutes	3 hours	2 hours	Extended <sup>1</sup>

<sup>1</sup> See International Protective Coatings Definitions & Abbreviations

**REGULATORY DATA**

<b>Flash Point</b>	Part A 111°F (44°C); Part B 81°F (27°C); Mixed 104°F (40°C)	
<b>Product Weight</b>	12.6 lb/gal (1.51 kg/l)	
<b>VOC</b>	2.54 lb/gal (305 g/l) 198 g/kg	EPA Method 24 EU Solvent Emissions Directive (Council Directive 1999/13/EC)

See Product Characteristics section for further details



**SURFACE PREPARATION**

The performance of this product will depend upon the degree of surface preparation. The surface to be coated should be clean, dry and free from contamination. Prior to paint application, all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Accumulated dirt and soluble salts must be removed. Dry bristle brushing will normally be adequate for accumulated dirt. Soluble salts should be removed by fresh water washing.

**Abrasive Blast Cleaning**

Interplus 356 may be applied to a surface abrasive blast cleaned to a minimum Sa1 (ISO 8501-1:2007) C or D grade rusting, or SSPC SP7.

**Hand or Power Tool Preparation**

Hand or power tool clean to a minimum St2 (ISO 8501-1:2007) or SSPC-SP2.

Note, all scale must be removed and areas which cannot be prepared adequately by chipping or needle gun should be spot blasted to a minimum standard of Sa2 (ISO 8501-1:2007) or SSPC-SP6 Typically this would apply to C or D grade rusting in this standard.

On steel surfaces operating at in-service temperatures up to 212°F (100°C) cleaning to a minimum St3 (ISO 8501-1:2007) or SSPC-SP3 is required for optimum performance.

**Ultra High Pressure Hydroblasting/Abrasive Wet Blasting**

May be applied to surfaces prepared to Sa2½ (ISO 8501-1:2007) or SSPC-SP6 which have flash rusted to no worse than Grade HB2½M (refer to International Hydroblasting Standards) or Grade SB2½M (refer to International Slurry Blasting Standards). It is also possible to apply to damp surfaces in some circumstances. Further information is available from International Protective Coatings.

**Aged Coatings**

Interplus 356 is suitable for overlap onto most aged coating systems. Loose or flaking coatings should be removed back to a firm edge. Glossy epoxies and polyurethanes may require abrasion.

**APPLICATION**

<b>Mixing</b>	Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed, it must be used within the working pot life specified.			
	(1) Agitate Base (Part A) with a power agitator.			
	(2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.			
<b>Mix Ratio</b>	3 part(s) : 1 part(s) by volume			
<b>Working Pot Life</b>	41°F (5°C)	59°F (15°C)	77°F (25°C)	104°F (40°C)
	8 hours	4 hours	2 hours	45 minutes
<b>Airless Spray</b>	Recommended	Tip Range 19-23 thou (0.48-0.58 mm) Total output fluid pressure at spray tip not less than 3000 psi (211 kg/cm <sup>2</sup> )		
<b>Air Spray (Pressure Pot)</b>	Recommended	Gun	DeVilbiss MBC or JGA	
		Air Cap	704 or 765	
		Fluid Tip	E	
<b>Brush</b>	Recommended	Typically 3.0-4.0 mils (75-100 microns) can be achieved		
<b>Roller</b>	Recommended	Typically 2.0-3.0 mils (50-75 microns) can be achieved		
<b>Thinner</b>	International GTA220 (or International GTA415)	May be necessary at low temperatures, see Product Characteristics. Do not thin more than allowed by local environmental legislation		
<b>Cleaner</b>	International GTA822 (or International GTA415)			
<b>Work Stoppages</b>	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA822. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.			
<b>Clean Up</b>	Clean all equipment immediately after use with International GTA822. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.			
	All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation			



**PRODUCT CHARACTERISTICS**

In order to ensure good anti-corrosive performance, it is important to achieve a minimum system dry film thickness of 8 mils (200 microns) by application of multi-coats over hand prepared steel.

When applying Interplus 356 by brush or roller, it may be necessary to apply multiple coats to achieve the total specified system dry film thickness.

**Wet Blasted (Damp Surfaces)**

If salt water is used in the wet blast process, the resulting surface must be thoroughly washed with fresh water before application of Interplus 356. With freshly blasted surfaces a slight degree of flash rusting is allowable, and is preferable to the surface being too wet. Puddles, ponding and accumulations of water must be removed.

To ensure good aged overcoating of Interplus 356 by other materials the surface must be clean, dry and free from contamination, particularly if the surface profile is rough due to the presence of micaceous iron oxide.

**Low Temperature Curing**

Interplus 356 is capable of curing at temperatures below 32°F (0°C). However, this product should not be applied at temperatures below 32°F(0°C ) where there is a possibility of ice formation on the substrate.

Temperature	Touch Dry	Hard Dry	Minimum overcoating interval with recommended topcoats	
			<i>Minimum</i>	<i>Maximum</i>
23°F (-5°C )	24 hours	60 hours	60 hours	Extended*
32°F (0°C)	16 hours	36 hours	36 hours	Extended*

\*See International Protective Coatings Definitions & Abbreviations

Touch dry times shown above are actual drying times due to chemical cure, rather than physical set due to solidification of the coating film at temperatures below 32°F (0°C).

At low temperatures, it may be necessary to thin Interplus 356 to enable airless spray application to be performed. Normally 5% thinning (by volume) with International GTA220 will be satisfactory for this purpose.

Interplus 356 is suitable for protection of steel operating at continuous dry temperatures of up to 302°F (150°C), with intermittent surges up to 392°F (200°C).

Interplus 356 is not designed for continuous water immersion.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in color and normal manufacturing tolerances.

**SYSTEMS COMPATIBILITY**

Interplus 356 will generally be applied to bare steel but is fully compatible for overlap onto most aged coatings, in addition to touch up repair of the following primers:

Intercure 200	Interzinc 12
Intergard 251	Interzinc 22
Intergard 269	Interzinc 42
InterH2O 280	Interzinc 52
Interseal 670HS	Interzinc 315

Recommended topcoats/intermediates are:

Intercure 420	Interplus 356
Interfine 629HS	Interplus 770
Interfine 878	Interplus 880
Interfine 979	Interseal 670HS
Interfine 1080	Interthane 990
Intergard 475HS	Interzone 505
Intergard 740	Interzone 954

It should be noted that Interplus 356 is not suitable for overcoating with thin films of alkyd, chlorinated rubber, vinyl or acrylic finishes.

For other suitable topcoats/intermediates consult International Protective Coatings.

**ADDITIONAL INFORMATION**

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at [www.international-pc.com](http://www.international-pc.com):

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

**SAFETY PRECAUTIONS**

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	20 liter	15 liter	20 liter	5 liter	5 liter
	5 US gal	3 US gal	5 US gal	1 US gal	1 US gal
For availability of other pack sizes contact International Protective Coatings					
SHIPPING WEIGHT	Unit Size	Part A	Part B		
	20 liter	27.7 kg	5.3 kg		
	5 US gal	56.2 lb	8.8 lb		
STORAGE	Shelf Life	12 months minimum at 77°F (25°C). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.			

**Disclaimer**

*The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local International Paint representative that this data sheet is current prior to using the product.*

*This Technical Data Sheet is available on our website at [www.international-marine.com](http://www.international-marine.com) or [www.international-pc.com](http://www.international-pc.com), and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.*

Issue date: 11/30/2011

Copyright © AkzoNobel, 11/30/2011.

 Copyright © AkzoNobel, 11/30/2011.

[www.international-pc.com](http://www.international-pc.com)

<u>Test Type</u>	<u>Test Method</u>	<u>Specification Details</u>	<u>Typical Results</u>
Adhesion	ISO 4624 - "Pull-off test for adhesion" using portable adhesion testers	1 x 150µm dft applied directly to Sa2½ blasted steel.	Not less than 10MPa (1450psi) when using a PAT Model GM01 hydraulic adhesion tester on 5mm thick steel.
Adhesion	ISO 4624 - "Pull-off test for adhesion" using portable adhesion testers	1 x 150µm applied directly over UHP HB2½ M-H prepared steel	Not less than 8MPa (1160psi) when using a PAT Model GM01 hydraulic adhesion tester on 5mm thick steel.
Condensation	ISO 6270 - "Resistance to continuous condensation @ 35°C"	1 x 125µm dft applied directly to Sa2½ blasted steel. (Topcoated with Interthane 870)	No film defects following 3000 hours exposure.
Cyclic Corrosion	Norsok M-501 Revision 2 "Norsok Cyclic Test"	1 x 300µm applied directly over UHP HB2½ M-H prepared steel. (Topcoated with Interfine 629HS)	No blistering, rusting, cracking etc and typically <5mm rust creep at the scribe following 4200hrs exposure.
Flexibility	ASTM D522 - "Mandrel Bend Test of Attached Organic Coatings" , - Conical Mandrel Test	1 x 125µm dft applied directly over abraded steel plate.	8% Elongation
Impact	ASTM D2794 - "Resistance to the Effects of Rapid Deformation (Impact)"	1 x 125µm dft applied directly to Sa2½ blasted steel.	Direct Impact Resistance - 3.5 Joules.
Salt Spray	BS 3900 Part F4 - "Resistance to continuous salt spray @ 20°C"	1 x 125µm dft applied directly to Sa2½ blasted steel. (Topcoated with Interthane 870)	No blistering, rusting, cracking etc and typically <2mm rust creep at the scribe following 3000hrs exposure.
Salt Spray	ASTM G85, Annex A5 - "Modified salt spray or Prohesion test"	1 x 250µm dft applied directly to Sa2½ blasted steel. (Topcoated with Interfine 629HS)	No blistering, rusting, cracking etc and typically <4mm rust creep at the scribe following 4000hrs exposure.
Salt Spray	ISO 9227 - "Corrosion tests in artificial atmospheres -- Salt spray tests"	1 x 200µm dft applied directly to Sa2½ blasted steel	Typically <5mm rust creep at the scribe following 3000 hours exposure.

Test Performance Results were obtained in a controlled laboratory environment, as specified in the Test Method. International Protective Coatings make no representation that the exhibited published test results, or any other tests, actually represent results found in all field environments

**PRODUCT DESCRIPTION**

A low VOC, high build, semi-gloss urethane finish with excellent gloss and color retention on exterior exposure, for use over correctly prepared and primed surfaces.

The VOC is below 250 g/l to conform to local VOC regulations.

**INTENDED USES**

Suitable for use both in new construction and as an industrial maintenance finish, Interthane 870UHS can be used in a wide variety of environments including steel infrastructure such as stadia and airports, offshore structures, petrochemical facilities, bridges, pulp and paper mills and in the power industry.

Particularly designed for use in areas where a semi-gloss finish is the preferred option.

Provides a versatile option where overcoating of intermediates in one coat is not possible using conventional thin film polyurethane finishes.

**PRACTICAL INFORMATION FOR INTERTHANE 870UHS**

<b>Color</b>	Wide range via the Chromascan® system
<b>Gloss Level</b>	Semi Gloss
<b>Volume Solids</b>	68% ± 3% (depends on color)
<b>Typical Thickness</b>	3-5 mils (75-125 microns) dry equivalent to 4.4-7.4 mils (110-184 microns) wet
<b>Theoretical Coverage</b>	218 sq.ft/US gallon at 5 mils d.f.t and stated volume solids 5.40 m <sup>2</sup> /liter at 125 microns d.f.t and stated volume solids
<b>Practical Coverage</b>	Allow appropriate loss factors
<b>Method of Application</b>	Airless Spray, Air Spray, Brush, Roller

**Drying Time**

Temperature	Touch Dry	Hard Dry	Overcoating Interval with recommended topcoats	
			Minimum	Maximum
32°F (0°C)	16 hours	30 hours	30 hours	Extended <sup>1</sup>
41°F (5°C)	6 hours	20 hours	20 hours	Extended <sup>1</sup>
77°F (25°C)	1.5 hours	6 hours	6 hours	Extended <sup>1</sup>
104°F (40°C)	1 hour	4 hours	4 hours	Extended <sup>1</sup>

<sup>1</sup> See International Protective Coatings Definitions & Abbreviations

**REGULATORY DATA**

<b>Flash Point</b>	Part A 100°F (38°C); Part B 122°F (50°C); Mixed 100°F (38°C)		
<b>Product Weight</b>	12.1 lb/gal (1.45 kg/l)		
<b>VOC</b>	1.91 lb/gal (230 g/l)	EPA Method 24	

See Product Characteristics section for further details



**SURFACE PREPARATION**

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application, all surfaces should be assessed and treated in accordance with ISO 8504:2000.

**Primed Surfaces**

Interthane 870UHS should always be applied over a recommended anti-corrosive coating scheme. The primer surface should be dry and free from all contamination, and Interthane 870UHS must be applied within the overcoating intervals specified (consult the relevant product data sheet).

Areas of breakdown, damage etc., should be prepared to the specified standard (e.g. SSPC-SP6 or Sa2½ (ISO 8501-1:2007), Abrasive Blasting, or SSPC-SP11, Power Tool Cleaning) and patch primed prior to the application of Interthane 870UHS.

**APPLICATION**

<b>Mixing</b>	Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified.			
	(1) Agitate Base (Part A) with a power agitator.			
	(2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.			
<b>Mix Ratio</b>	7 part(s) : 1 part(s) by volume			
<b>Working Pot Life</b>	32°F (0°C) 7 hours	41°F (5°C) 7 hours	77°F (25°C) 1.5 hours	104°F (40°C) 30 minutes
<b>Airless Spray</b>	Recommended	Tip Range 15-21 thou (0.38-0.53 mm) Total output fluid pressure at spray tip not less than 2503 psi (176 kg/cm <sup>2</sup> )		
<b>Air Spray (Pressure Pot)</b>	Recommended	Gun Air Cap Fluid Tip	DeVilbiss MBC or JGA 704 or 765 E	
<b>Air Spray (Conventional)</b>	Suitable	Use suitable proprietary equipment.		
<b>Brush</b>	Suitable	Typically 2.0-3.0 mils (50-75 microns) can be achieved		
<b>Roller</b>	Suitable	Typically 2.0-3.0 mils (50-75 microns) can be achieved		
<b>Thinner</b>	International GTA056 (or International GTA713)	Do not thin more than allowed by local environmental legislation		
<b>Cleaner</b>	International GTA056 (or International GTA713)			
<b>Work Stoppages</b>	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA056. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units			
<b>Clean Up</b>	Clean all equipment immediately after use with International GTA056. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.			
	All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation			

**PRODUCT CHARACTERISTICS**

Level of sheen and surface finish is dependent on application method. Avoid using a mixture of application methods whenever possible.

Maximum film build in one coat is best attained by airless spray. When applying by methods other than airless spray, the required film build is unlikely to be achieved. Application by air spray may require a multiple cross spray pattern to attain maximum film build. Lower or high temperatures may require specific application techniques to achieve maximum film build.

If application in one coat using brush and roller is desired then the undercoat shade should be chosen to match the final coat shades. Dark colored and MIO undercoats will typically require 2 coats of Interthane 870UHS.

When applying Interthane 870UHS by brush or roller, it may be necessary to apply multiple coats to achieve the total specified system dry film thickness.

Applicators should be aware that the ability to apply Interthane 870UHS in one coat will be affected by the temperature of the substrate. At higher steel temperatures, lower film builds and thinner coats are likely to be achieved.

This product must only be thinned using the recommended International thinners. The use of alternative thinners, particularly those containing alcohols, can severely inhibit the curing mechanism of the coating.

When applying Interthane 870UHS in confined spaces, ensure adequate ventilation.

When overcoating after weathering, or aging, ensure the coating is fully cleaned to remove all surface contamination such as oil, grease, salt crystals and traffic fumes, before application of a further coat of Interthane 870UHS.

Do not apply at steel temperatures below 41°F (5°C).

Surface temperature must always be a minimum of 5°F (3°C) above dew point.

It is recommended that relative humidity should not exceed 85% during application and cure.

Condensation occurring during or immediately after application may result in a matte finish and an inferior film.

Premature exposure to ponding water will cause color change, especially in dark colors and at low temperatures.

Absolute measured adhesion of topcoats to aged Interthane 870UHS is less than that to fresh material, however, it is adequate for the specified end use.

This product is not recommended for use in immersion conditions. When severe chemical or solvent splashing is likely to occur, contact International Protective Coatings for information regarding suitability.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in color and normal manufacturing tolerances.

Low molecular weight reactive additives, which will form part of the film during normal ambient cure conditions, will also affect VOC values determined using EPA Method 24.

**SYSTEMS COMPATIBILITY**

---

The following primers/intermediates are recommended for Interthane 870UHS:

Intercure 200HS	Interzinc 315
Intergard 251	Interzinc 52
Intergard 475HS	Interzinc 52HS
Interplus 256	Interzone 1000
Interplus 356	Interzone 505
Interseal 670HS	Interzone 954

For other suitable primer/intermediates, consult International Protective Coatings.

Interthane 870UHS is designed to be topcoated with itself.

**ADDITIONAL INFORMATION**

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at [www.international-pc.com](http://www.international-pc.com):

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

**SAFETY PRECAUTIONS**

**Warning: Contains isocyanate. Wear air-fed hood for spray application.**

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	5 US gal	4.38 US gal	5 US gal	0.63 US gal	1 US gal
For availability of other pack sizes contact International Protective Coatings					
SHIPPING WEIGHT	Unit Size	Part A		Part B	
		57.5 lb		6.4 lb	
	5 US gal	57.5 lb		6.4 lb	
STORAGE	Shelf Life	12 months minimum at 77°F (25°C). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.			

**Important Note**

*The information in this data sheet is not intended to be exhaustive: any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to law) any loss or damage arising out of the use of the product. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local International Paint representative that this data sheet is current prior to using the product.*

Issue date: 9/18/2009

Copyright © AkzoNobel, 9/18/2009.

 Copyright © AkzoNobel, 9/18/2009.

[www.international-pc.com](http://www.international-pc.com)

# QTA044\_A2

Material Safety Data Sheet  
 INTERTHANE 870UHS BASE ULTRA DEEP PART A

Sales  
 Order: {SalesOrd}  
 QTA044  
 05/13/2011  
 A2-3

Bulk Sales Reference No.:  
 MSDS Revision Date:  
 MSDS Revision Number:



1. Identification of the preparation and company

Product Identity INTERTHANE 870UHS BASE ULTRA DEEP PART A  
 Bulk Sales Reference No. QTA044  
 Company Name International Paint LLC  
 6001 Antoine Drive  
 Houston Texas 77091

Emergency  
 CHEMTREC (USA) (800) 424-9300  
 International Paint (713) 682-1711  
 Poison Control Center (800) 854-6813  
 Customer Service  
 International Paint (800) 589-1267  
 Fax No. (800) 631-7481

2. Hazard identification of the product



Danger

GHS Classification;

Item	Category	Hazard
Flammability	3	Flammable liquid and vapor
Acute Toxicity (mouth)	Not classified	Not applicable
Acute Toxicity (skin)	Not classified	Not applicable
Acute Toxicity (inhalation)	Not classified	Not applicable
Acute Toxicity (ingestion)	Not classified	Not applicable
Skin corrosion/irritation	Not classified	Not applicable
Eye damage/irritation	Not classified	Not applicable
Sensitization (respiratory)	Not classified	Not applicable
Sensitization (skin)	Not classified	Not applicable
Germ toxicity	Not classified	Not applicable
Specific target organ systemic toxicity (single exposure)	1	central nerve system
	2	Not applicable
	3	narcotic effects, respiratory tract irritation
Specific target organ systemic Toxicity (repeated exposure)	1	Not applicable
	2	Not applicable
Aspiration hazard	Not classified	Not applicable
Harmfulness to aquatic Environment (acute)	Not classified	Not applicable
	Not classified	Not applicable



## QTA044\_A2

Harmfulness to aquatic Environment (long term effect)		
Carcinogenicity	1A	May cause cancer
Reproductive Toxicity	Not classified	Not applicable
Organic Peroxide	Not classified	Not applicable

Safety Phrases: Not Applicable

Overview	NOTICE: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal. Avoid contact with eyes, skin and clothing.			
Inhalation	Harmful if inhaled. Causes nose and throat irritation. Vapors may affect the brain or nervous system causing dizziness, headache or nausea.			
Eyes	Causes severe eye irritation. Avoid contact with eyes.			
Skin	Causes skin irritation. May be harmful if absorbed through the skin.			
Ingestion	Harmful if swallowed. May cause abdominal pain, nausea, vomiting, diarrhea, or drowsiness.			
Chronic effects	Cancer hazard. Contains an ingredient which can cause cancer (See Section 2 and Section 15 for each ingredient). Risk of cancer depends on duration and level of exposure.			
HMIS Rating	Health: 2	Flammability: 2	Reactivity: 0	PPE: X

### 3. Composition/information on ingredients

Ingredient	CAS No.	Percent
p-Chloro-a,a,a-trifluorotoluene	000098-56-6	1.0 - 10
Methyl n-amyl ketone	0000110-43-0	1.0 - 10
BUTYL ACETATE	0000123-86-4	1.0 - 10
Ethyl 3-ethoxypropionate	0000763-69-9	1.0 - 10
Limestone	0001317-65-3	25 - 50
ZEOLITE	0001318-02-1	1.0 - 10
Silica, amorphous	0007631-86-9	1.0 - 10
Talc (*non-asbestiform)	14807-96-6*	1.0 - 10

### 4. First aid measures

General	Remove contaminated clothing and shoes. Get medical attention immediately. Wash clothing before reuse. Thoroughly clean or destroy contaminated shoes.
Inhalation	If inhaled, remove to fresh air. If not breathing, give artificial respiration. If breathing is difficult, give oxygen. Get medical attention immediately.
Eyes	In case of contact, immediately flush eyes with plenty of water for at least 15 minutes. Get medical attention immediately.
Skin	In case of contact, immediately flush skin with soap and plenty of water. Get medical attention immediately.
Ingestion	If swallowed, immediately contact Poison Control Center at 1-800-854-6813. DO NOT induce vomiting unless instructed to do so by medical personnel. Never give anything by mouth to an unconscious person.

### 5. Fire-fighting measures

Flash Point	F: 100 C: 38
Lower Explosive Limit (LEL)	.9 (%vol in air) at Normal Atmospheric Temp and Pressure
ERG Guide No.	128

QTA044\_A2

6. Accidental release measures

Spill Response Procedures	ELIMINATE ALL IGNITION SOURCES (no smoking, flares, sparks or flames in immediate area). Use only non-sparking equipment to handle spilled material and absorbent. Do not touch or walk through spilled material. Stop leak if you can do so without risk. Prevent entry into waterways, sewers, basements or confined areas. A vapor suppressing foam may be used to reduce vapors. Absorb or cover with dry earth, sand, or other non-combustible material and transfer to containers. Use non-sparking tools to collect absorbed material.
Public Safety	CALL CHEMTREC at (800)–424–9300 for emergency response. Isolate spill or leak area immediately for at least 50 meters (150 feet) in all directions. Keep unauthorized personnel away. Stay upwind. Keep out of low areas. Ventilate closed spaces before entering. LARGE SPILLS: Consider initial downwind evacuation for at least 300 meters (1000 feet).
ERG Guide No.	128

7. Handling and storage

Storage Temperature	Store between 40–100F (4–38C).
Handling and Storage Precautions	Keep away from heat, sparks and flame. Do not smoke. Extinguish all flames and pilot lights, and turn off stoves, heaters, electric motors and other sources of ignition during use and until all vapors are gone. Vapors may cause flash fire or ignite explosively. Prevent build-up of vapors by opening all windows and doors to achieve cross-ventilation. Avoid contact with eyes and clothing. Avoid prolonged or repeated contact with skin. Close container after each use. Wash thoroughly after handling.

8. Exposure controls and personal protection

		Exposure	
CAS No.	Ingredient	Source	Value
0000098–56–6	p-Chloro-a,a,a-trifluorotoluene	OSHA	No Established Limit
		ACGIH	No Established Limit
		NIOSH	No Established Limit
		Supplier	No Established Limit
		OHSA, CAN	No Established Limit
		Mexico	No Established Limit
		Brazil	No Established Limit
0000110–43–0	Methyl n-amil ketone	OSHA	100 ppm TWA; 465 mg/m3 TWA
		ACGIH	50 ppm TWA
		NIOSH	100 ppm TWA; 465 mg/m3 TWA800 ppm IDLH
		Supplier	No Established Limit
		OHSA, CAN	25 ppm TWA; 115 mg/m3 TWA
		Mexico	50 ppm TWA; 235 mg/m3 TWA100 ppm STEL; 465 mg/m3 STEL
		Brazil	No Established Limit
0000123–86–4	BUTYL ACETATE	OSHA	150 ppm TWA; 710 mg/m3 TWA200 ppm STEL; 950 mg/m3 STEL
		ACGIH	150 ppm TWA200 ppm STEL
		NIOSH	150 ppm TWA; 710 mg/m3 TWA200 ppm STEL; 950 mg/m3 STEL1700 ppm IDLH (10% LEL)
		Supplier	No Established Limit
		OHSA, CAN	150 ppm TWA200 ppm STEL
		Mexico	150 ppm TWA; 710 mg/m3 TWA200 ppm STEL; 950 mg/m3 STEL
		Brazil	No Established Limit
0000763–69–9	Ethyl 3-ethoxypropionate	OSHA	No Established Limit
		ACGIH	No Established Limit
		NIOSH	No Established Limit

## QTA044\_A2

		Supplier	No Established Limit
		OHSA, CAN	50 ppm TWA; 300 mg/m3 TWA
		Mexico	No Established Limit
		Brazil	No Established Limit
0001317-65-3	Limestone	OSHA	15 mg/m3 TWA (total dust); 5 mg/m3 TWA (respirable fraction)
		ACGIH	No Established Limit
		NIOSH	10 mg/m3 TWA (total dust); 5 mg/m3 TWA (respirable dust)
		Supplier	No Established Limit
		OHSA, CAN	No Established Limit
		Mexico	10 mg/m3 TWA 20 mg/m3 STEL
		Brazil	No Established Limit
0001318-02-1	ZEOLITE	OSHA	No Established Limit
		ACGIH	No Established Limit
		NIOSH	No Established Limit
		Supplier	No Established Limit
		OHSA, CAN	No Established Limit
		Mexico	No Established Limit
		Brazil	No Established Limit
0007631-86-9	Silica, amorphous	OSHA	No Established Limit
		ACGIH	No Established Limit
		NIOSH	6 mg/m3 TWA 3000 mg/m3 IDLH
		Supplier	No Established Limit
		OHSA, CAN	No Established Limit
		Mexico	No Established Limit
		Brazil	No Established Limit
14807-96-6*	Talc (*non-asbestiform)	OSHA	No Established Limit
		ACGIH	No Established Limit
		NIOSH	No Established Limit
		Supplier	No Established Limit
		OHSA, CAN	No Established Limit
		Mexico	No Established Limit
		Brazil	No Established Limit

## Health Data

CAS No.	Ingredient	Source	Value
0000098-56-6	p-Chloro-a,a,a-trifluorotoluene	NIOSH	No Established Limit
0000110-43-0	Methyl n-amyl ketone	NIOSH	Irritation; liver kidney
0000123-86-4	BUTYL ACETATE	NIOSH	Mucous membrane and eye irritation; high concentrations cause nervous system effects in animals
0000763-69-9	Ethyl 3-ethoxypropionate	NIOSH	No Established Limit
0001317-65-3	Limestone	NIOSH	Eye and skin irritation Physical irritation
0001318-02-1	ZEOLITE	NIOSH	No Established Limit
0007631-86-9	Silica, amorphous	NIOSH	No Established Limit
14807-96-6*	Talc (*non-asbestiform)	NIOSH	No Established Limit

## Carcinogen Data

CAS No.	Ingredient	Source	Value
0000098-56-6	p-Chloro-a,a,a-trifluorotoluene	OSHA	Select Carcinogen: No
		NTP	Known: No; Suspected: No
		IARC	Group 1: No; Group 2a: No; Group 2b: No; Group 3: No; Group 4: No;

QTA044\_A2

0000110-43-0	Methyl n-amyl ketone	OSHA	Select Carcinogen: No
		NTP	Known: No; Suspected: No
		IARC	Group 1: No; Group 2a: No; Group 2b: No; Group 3: No; Group 4: No;
0000123-86-4	BUTYL ACETATE	OSHA	Select Carcinogen: No
		NTP	Known: No; Suspected: No
		IARC	Group 1: No; Group 2a: No; Group 2b: No; Group 3: No; Group 4: No;
0000763-69-9	Ethyl 3-ethoxypropionate	OSHA	Select Carcinogen: No
		NTP	Known: No; Suspected: No
		IARC	Group 1: No; Group 2a: No; Group 2b: No; Group 3: No; Group 4: No;
0001317-65-3	Limestone	OSHA	Select Carcinogen: No
		NTP	Known: No; Suspected: No
		IARC	Group 1: No; Group 2a: No; Group 2b: No; Group 3: No; Group 4: No;
0001318-02-1	ZEOLITE	OSHA	Select Carcinogen: No
		NTP	Known: No; Suspected: No
		IARC	Group 1: No; Group 2a: No; Group 2b: No; Group 3: Yes; Group 4: No;
0007631-86-9	Silica, amorphous	OSHA	Select Carcinogen: No
		NTP	Known: No; Suspected: No
		IARC	Group 1: No; Group 2a: No; Group 2b: No; Group 3: Yes; Group 4: No;
14807-96-6*	Talc (*non-asbestiform)	OSHA	Select Carcinogen: No
		NTP	Known: No; Suspected: No
		IARC	Group 1: No; Group 2a: No; Group 2b: No; Group 3: No; Group 4: No;

Respiratory	Select equipment to provide protection from the ingredients listed in Section 3 of this document. Ensure fresh air entry during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates dust, vapor, or mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow respirator manufacturer's directions for respirator use. FOR USERS OF 3M RESPIRATORY PROTECTION ONLY: For information and assistance on 3M occupational health and safety products, call OH&ESD Technical Service toll free in U.S.A. 1-800-243-4630, in Canada call 1-800-267-4414. Please do not contact these numbers regarding other manufacturer's respiratory protection products. 3M does not endorse the accuracy of the information contained in this Material Safety Data Sheet.
Eyes	Avoid contact with eyes. Protective equipment should be selected to provide protection from exposure to the chemicals listed in Section 3 of this document. Depending on the site-specific conditions of use, safety glasses, chemical goggles, and/or head and face protection may be required to prevent contact. The equipment must be thoroughly cleaned, or discarded after each use.
Skin	Protective equipment should be selected to provide protection from exposure to the chemicals listed in Section 3 of this document. Depending on the site-specific conditions of use, protective gloves, apron, boots, head and face protection may be required to prevent contact. The equipment must be thoroughly cleaned, or discarded after each use.
Engineering Controls	Prevent build-up of vapors by opening all windows and doors to achieve cross-ventilation.
Other Work Practices	Emergency eye wash fountains and safety showers should be available in the immediate vicinity of any potential exposure. Use good personal hygiene practices. Wash hands before eating, drinking, using toilet facilities, etc. Promptly remove soiled clothing and wash clothing thoroughly before reuse. Shower after work using plenty of soap and water.

9. Physical and chemical properties

Physical State	Liquid Coloured
pH	No Established Limit
Specific Gravity	1.36



QTA044\_A2

Boiling Point F 140  
 Vapor Density Heavier than air  
 VOC % Refer to the Technical Data Sheet or label where information is available.  
 Evaporation Rate Slower than ether

10. Stability and reactivity

General This product is stable and hazardous polymerization will not occur. Not sensitive to mechanical impact. Excessive heat and fumes generation can occur if improperly handled.  
 Incompatible Materials Strong oxidizing agents.  
 Hazardous Decomposition May produce hazardous fumes when heated to decomposition as in welding. Fumes may produce Carbon Dioxide and Carbon Monoxide.

11. Toxicological information

Ingredient	Oral LD50, mg/kg	Skin LD50, mg/kg	Inhalation Vapor LD50, mg/L/4hr
p-Chloro-a,a,a-trifluorotoluene – (0000098-56-6)	13,000.00, Rat – Category: NA	2,700.00, Rabbit – Category: 5	33.00, Rat – Category: NA
Methyl n-amyl ketone – (0000110-43-0)	1,670.00, Rat – Category: 4	-----	-----
BUTYL ACETATE – (0000123-86-4)	10,768.00, Rat – Category: NA	17,600.00, Rabbit – Category: NA	-----
Ethyl 3-ethoxypropionate – (0000763-69-9)	3,200.00, Rat – Category: 5	-----	-----
Limestone – (0001317-65-3)	-----	-----	-----
ZEOLITE – (0001318-02-1)	-----	2,000.00, Rabbit – Category: 4	-----
Silica, amorphous – (0007631-86-9)	5,000.00, Rat – Category: 5	2,000.00, Rabbit – Category: 4	-----
Talc (*non-asbestiform) – (14807-96-6*)	-----	-----	-----

General NOTICE: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal. No additional information provided for this product. See Sections 8 and 11 for chemical specific data.

12. Ecological information

No additional information provided for this product. See Sections 8 and 11 for chemical specific data.

13. Disposal considerations

Dispose of in accordance with local, state and federal regulations. (Also reference RCRA information in Section 15 if listed).

14. Transport information

DOT (Domestic Surface Transportation)		IMO / IMDG (Ocean Transportation)	
DOT Proper Shipping Name	PAINT	IMDG Proper Shipping Name	PAINT
DOT Hazard Class	3	IMDG Hazard Class	3 – Flammable and Combustible liquid
UN / NA Number	UN 1263	UN / NA Number	UN 1263
DOT Packing Group	III	IMDG Packing Group	III
CERCLA/DOT RQ	5427 gal. / 61488 lbs.	System Reference Code	2

15. Regulatory information

## QTA044\_A2

Regulatory Overview            The regulatory data in Section 15 is not intended to be all-inclusive, only selected regulations are represented. All ingredients of this product are listed on the TSCA (Toxic Substance Control Act) Inventory or are not required to be listed on the TSCA Inventory.

WHMIS Classification            B3:D2B

DOT Marine Pollutants (10%):  
(No Product Ingredients Listed)

DOT Severe Marine Pollutants (1%):  
(No Product Ingredients Listed)

EPCRA 311/312 Chemicals and RQs (>.1%) :

    BUTYL ACETATE    (5000 lb final RQ; 2270 kg final RQ)

EPCRA 302 Extremely Hazardous (>.1%) :

(No Product Ingredients Listed)

EPCRA 313 Toxic Chemicals (>.1%) :

(No Product Ingredients Listed)

Mass RTK Substances (>1%) :

    Limestone

    Methyl n-amyl ketone

    BUTYL ACETATE

    Silica, amorphous

Mass Extraordinarily Haz Sub (>.01%) :

    Quartz

    Silica, cristobalite

Penn RTK Substances (>1%) :

    Limestone

    Methyl n-amyl ketone

    BUTYL ACETATE

    Silica, amorphous

Penn Special Hazardous Substances (>.01%) :

(No Product Ingredients Listed)

Rhode Island Hazardous Substances (>.1%) :

    Limestone

    Methyl n-amyl ketone

    BUTYL ACETATE

    Stoddard solvent

RCRA Status:

(No Product Ingredients Listed)

N.J. RTK Substances (>1%) :

    Limestone

    Methyl n-amyl ketone

    BUTYL ACETATE

N.J. Special Hazardous Substances (>.01%) :

    Benzene, ethyl-

    Isobutyl alcohol

    BUTYL ACETATE

    Quartz

    Silica, cristobalite

    Xylenes (o-, m-, p- isomers)

N.J. Env. Hazardous Substances (>.1%) :

(No Product Ingredients Listed)

Proposition 65 – Carcinogens (>0%):

    Benzene, ethyl-

    Formaldehyde

    Quartz

Proposition 65 – Female Repro Toxins (>0%):

(No Product Ingredients Listed)

## QTA044\_A2

Proposition 65 – Male Repro Toxins (>0%):  
(No Product Ingredients Listed)

Proposition 65 – Developmental Toxins (>0%):  
(No Product Ingredients Listed)

Risk Phrases:

R45: May cause cancer.

16. Other information
-----------------------

The information and recommendations contained herein are based upon data believed to be correct. However, no guarantee or warranty of any kind, expressed or implied, is made with respect to the information contained herein. We accept no responsibility and disclaim all liability for any harmful effects which may be caused by exposure to our products. Customers/users of this product must comply with all applicable health and safety laws, regulations, and orders.

MATERIAL SAFETY DATA SHEET

Sales Order: {SalesOrd}

INTERTHANE 870/870UHS PART B

MSDS Revision No: A0 -9  
MSDS Revision Date: 07/28/2006



International Paint LLC

6001 Antoine Drive

Houston, Texas 77091

EMERGENCY NUMBERS:

(800) 424-9300 CHEMTREC (USA)  
(703) 527-3887 CHEMTREC (Intl)  
(800) 854-6813 Poison Control Center  
CUSTOMER SERVICE: (Non-Emergency)  
(800) 589-1267 International Paint  
(800) 631-7481 Interlux

1. GENERAL INFORMATION

Product Identity: INTERTHANE 870/870UHS PART B

Bulk Sales Reference No: QGA046

IMPORTANT: Read this MSDS before handling or disposing of this product, and provide this information to the employee, customers, and users of this product. PLEASE NOTE THE MSDS REVISION NUMBER AT THE TOP OF THIS PAGE. If the MSDS Revision Number posted at the top of this page does not match the MSDS Revision Number on the product label, please contact Customer Service at the phone number included above for the correct MSDS. This product is covered by the OSHA Hazard Communication Standard and this document has been prepared in accordance with requirements of this standard.

NOTICE: OSHA hazardous chemicals are listed in Section 2 if present at 1% or more. Carcinogens and extraordinarily/special hazardous chemicals are listed in Section 2 if present at .1% or more. Additional regulatory information for specific chemical categories is included in Section 15.

2. HAZARDOUS INGREDIENT INFORMATION

CAS No.	Ingredient Name & %	Source	Exposure Data
000095-63-6	Pseudocumene 1.0 - 10% by Weight	OSHA:	No Established Limit
		ACGIH:	No Established Limit
		NIOSH:	25 ppm TWA; 125 mg/m3 TWA
		Supplier:	No Established Limit
		OHSA, CAN:	No Established Limit
		Mexico:	No Established Limit
		Brazil:	No Established Limit
		Source	Health Data
		NIOSH:	No Established Limit
		Source	Carcinogen Data
		OSHA:	Select Carcinogen: No
		NTP:	Known Carcinogen: No; Suspected Carcinogen: No
		IARC:	Group 1: No; Group 2A: No; Group 2b: No; Group 3: No; Group 4: No

CAS No.	Ingredient Name & %	Source	Exposure Data
000108-67-8	TRIMETHYLBENZENE 1.0 - 10% by Weight	OSHA:	No Established Limit
		ACGIH:	No Established Limit
		NIOSH:	25 ppm TWA; 125 mg/m3 TWA
		Supplier:	No Established Limit
		OHSA, CAN:	No Established Limit
		Mexico:	No Established Limit
		Brazil:	No Established Limit
		Source	Health Data
		NIOSH:	No Established Limit
		Source	Carcinogen Data
		OSHA:	Select Carcinogen: No
		NTP:	Known Carcinogen: No; Suspected Carcinogen: No
		IARC:	Group 1: No; Group 2A: No; Group 2b: No; Group 3: No; Group 4: No



QGA046\_A0

CAS No.	Ingredient Name & %	Source	Exposure Data
028182-81-2	Hexamethylene diisocyanate homopolymer 50 – 75% by Weight	OSHA:	No Established Limit
		ACGIH:	No Established Limit
		NIOSH:	No Established Limit
		Supplier:	No Established Limit
		OHSA, CAN:	No Established Limit
		Mexico:	No Established Limit
		Brazil:	No Established Limit
		Source	Health Data
		NIOSH:	No Established Limit
		Source	Carcinogen Data
		OSHA:	Select Carcinogen: No
		NTP:	Known Carcinogen: No; Suspected Carcinogen: No
		IARC:	Group 1: No; Group 2A: No; Group 2b: No; Group 3: No; Group 4: No

CAS No.	Ingredient Name & %	Source	Exposure Data
064742-95-6	Petroleum naphtha, light aromatic 10 – 25% by Weight	OSHA:	No Established Limit
		ACGIH:	No Established Limit
		NIOSH:	No Established Limit
		Supplier:	No Established Limit
		OHSA, CAN:	No Established Limit
		Mexico:	No Established Limit
		Brazil:	No Established Limit
		Source	Health Data
		NIOSH:	No Established Limit
		Source	Carcinogen Data
		OSHA:	Select Carcinogen: No
		NTP:	Known Carcinogen: No; Suspected Carcinogen: No
		IARC:	Group 1: No; Group 2A: No; Group 2b: No; Group 3: No; Group 4: No

3. HAZARD IDENTIFICATION

Overview:	NOTICE: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal. Avoid contact with eyes, skin and clothing. Contains 1,2,4-Trimethylbenzene which can cause central nervous system depression, anemia and bronchitis.		
Inhalation:	May be harmful or fatal if inhaled. May cause lung injury. Causes nose and throat irritation. Vapors may affect the brain or nervous system causing dizziness, headache or nausea.		
Eyes:	Causes severe eye irritation. Avoid contact with eyes.		
Skin:	Causes skin irritation. May cause allergic skin reaction. May be harmful if absorbed through the skin.		
Ingestion:	Harmful if swallowed. May cause abdominal pain, nausea, vomiting, diarrhea, or drowsiness.		
Chronic Effects:	Contains an ingredient which can cause organ damage (See Section 2 and Section 15 for each ingredient). Cancer hazard. Contains an ingredient which can cause cancer (See Section 2 and Section 15 for each ingredient). Risk of cancer depends on duration and level of exposure.		
HMIS Rating:	Health: 2	Flammability: 2	Reactivity: 0

4. FIRST AID MEASURES

General:	Remove contaminated clothing and shoes. Get medical attention immediately. Wash clothing before reuse. Thoroughly clean or destroy contaminated shoes.
Inhalation:	If inhaled, remove to fresh air. If not breathing, give artificial respiration. If breathing is difficult, give oxygen. Get medical attention immediately.
Eyes:	In case of contact, immediately flush eyes with plenty of water for at least 15 minutes. Get medical attention immediately.
Skin:	In case of contact, immediately flush skin with soap and plenty of water. Get medical attention immediately.

## QGA046\_A0

Ingestion: If swallowed, immediately contact Poison Control Center at 1-800-854-6813. DO NOT induce vomiting unless instructed to do so by medical personnel. Never give anything by mouth to an unconscious person.

### 5. PROTECTIVE EQUIPMENT AND CONTROL MEASURES

Respiratory:	Select equipment to provide protection from the ingredients listed in Section 2 of this document. Ensure fresh air entry during application and drying. If you experience eye watering, headache or dizziness or if air monitoring demonstrates dust, vapor, or mist levels are above applicable limits, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow respirator manufacturer's directions for respirator use. FOR USERS OF 3M RESPIRATORY PROTECTION ONLY: For information and assistance on 3M occupational health and safety products, call OH&ESD Technical Service toll free in U.S.A. 1-800-243-4630, in Canada call 1-800-267-4414. Please do not contact these numbers regarding other manufacturer's respiratory protection products. 3M does not endorse the accuracy of the information contained in this Material Safety Data Sheet. INDIVIDUALS WITH LUNG OR BREATHING PROBLEMS OR PRIOR REACTION TO ISOCYANATES MUST NOT BE EXPOSED TO VAPOR OR SPRAY MIST. Do not breathe vapor or spray mist. Wear an appropriate, properly fitted respirator (NIOSH approved) during and after application unless air monitoring demonstrates vapor/mist levels are below applicable limits. A supplied air respirator (either positive pressure or continuous flow type) is required. Follow manufacturer's directions for respirator use and observe requirements specified in 29 CFR 1910.134.
Eyes:	Avoid contact with eyes. Protective equipment should be selected to provide protection from exposure to the chemicals listed in Section 2 of this document. Depending on the site-specific conditions of use, safety glasses, chemical goggles, and/or head and face protection may be required to prevent contact. The equipment must be thoroughly cleaned, or discarded after each use.
Skin/Hand:	Protective equipment should be selected to provide protection from exposure to the chemicals listed in Section 2 of this document. Depending on the site-specific conditions of use, protective gloves, apron, boots, head and face protection may be required to prevent contact. The equipment must be thoroughly cleaned, or discarded after each use.
Engineering Controls:	Prevent build-up of vapors by opening all windows and doors to achieve cross-ventilation.
Other Work Practices:	Emergency eye wash fountains and safety showers should be available in the immediate vicinity of any potential exposure. Use good personal hygiene practices. Wash hands before eating, drinking, using toilet facilities, etc. Promptly remove soiled clothing and wash clothing thoroughly before reuse. Shower after work using plenty of soap and water.

### 6. FIRE AND EXPLOSION INFORMATION

Flash Point:	F: 122 C: 50
Lower Explosive Limit (LEL):	1 (%vol in air) at Normal Atmospheric Temp and Pressure
Fire and Explosion Hazards:	Combustible liquid and vapor. FLAMMABLE/COMBUSTIBLE MATERIALS: Will be easily ignited by heat, sparks or flames. Vapors may form explosive mixtures with air. Vapors may travel to source of ignition and flash back. Most vapors are heavier than air. They will spread along ground and collect in low or confined areas (sewers, basements, tanks) creating a vapor explosion hazard. Runoff to sewers may create fire or explosion hazard. Containers may explode when heated.
Fire Fighting Procedures:	CAUTION: This product has a very low flashpoint. Use of water spray when fighting fire may be inefficient. SMALL FIRES: Use dry chemical, CO <sub>2</sub> , water spray or alcohol-resistant foam. LARGE FIRES: Use water spray, fog, or alcohol-resistant foam. Do not use straight streams. Move containers from fire area if you can do so without risk. Runoff from fire control may cause pollution. Dike fire control water for later disposal. Do not scatter the material. Also Reference Emergency Response Guide Number: 127

### 7. PHYSICAL AND CHEMICAL PROPERTIES

Physical State:	Liquid
pH:	No Established Limit
Specific Gravity:	1.064985
Boiling Point (F):	300
Vapor Density:	Heavier than air
VOC Content (lbs):	Refer to the Technical Data Sheet for this product.
Evaporation Rate:	Slower than ether

### 8. STABILITY AND REACTIVITY DATA

## QGA046\_A0

General:	This product is stable and hazardous polymerization will not occur.
Incompatible Materials:	Strong oxidizing agents.
Hazardous Decomposition:	May produce hazardous fumes when heated to decomposition as in welding. Fumes may produce Carbon Dioxide and Carbon Monoxide.

### 9. HANDLING AND STORAGE

Storage Temperature:	Store between 32 and 120 F
Handling and Storage Precautions:	Keep away from heat, sparks and flame. Do not smoke. Extinguish all flames and pilot lights, and turn off stoves, heaters, electric motors and other sources of ignition during use and until all vapors are gone. Vapors may cause flash fire or ignite explosively. Prevent build-up of vapors by opening all windows and doors to achieve cross-ventilation. Avoid contact with eyes, skin and clothing. Close container after each use. Wash thoroughly after handling.

### 10. TOXICOLOGICAL DATA

General:	NOTICE: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal. No additional information provided for this product. See Section 2 for chemical specific data.
----------	---

### 11. ECOLOGICAL DATA

General:	No additional information provided for this product. See Section 2 for chemical specific data.
----------	--

### 12. ACCIDENTAL RELEASE MEASURES

Spill Response Procedures:	ELIMINATE ALL IGNITION SOURCES (no smoking, flares, sparks or flames in immediate area). Use only non-sparking equipment to handle spilled material and absorbent. Do not touch or walk through spilled material. Stop leak if you can do so without risk. Prevent entry into waterways, sewers, basements or confined areas. A vapor suppressing foam may be used to reduce vapors. Absorb or cover with dry earth, sand, or other non-combustible material and transfer to containers. Use non-sparking tools to collect absorbed material. CALL CHEMTREC at (800)-424-9300 for emergency response. Isolate spill or leak area immediately for at least 25 to 50 meters (80 to 160 feet) in all directions. Keep unauthorized personnel away. Stay upwind. Keep out of low areas. Ventilate closed spaces before entering. LARGE SPILLS: Consider initial downwind evacuation for at least 300 meters (1000 feet). Also, Reference Emergency Response Guide Number: 127
Public Safety:	

### 13. DISPOSAL CONSIDERATION

Waste Disposal:	Dispose of in accordance with local, state and federal regulations. (Also reference RCRA information in Section 15 if listed).
-----------------	--

### 14. TRANSPORTATION INFORMATION

DOT (Domestic Surface Transportation)		IMO / IMDG (Ocean Transportation)	
DOT Proper Shipping Name:	PAINT	IMDG Proper Shipping Name:	PAINT
DOT Hazard Class:	3	IMDG Hazard Class:	3.3 – High flashpoint flammable liquids
UN / NA Number:	UN 1263	UN Number:	UN 1263
DOT Packing Group:	III	IMDG Packing Group:	III
CERCLA/DOT RQ:	1366 gal. / 12121 lbs.	System Reference Code:	2

### 15. REGULATORY INFORMATION

Regulatory Overview:	<p>The regulatory data in Section 15 is not intended to be all-inclusive, only selected regulations are represented. All ingredients of this product are listed on the TSCA (Toxic Substance Control Act) Inventory or are not required to be listed on the TSCA Inventory.</p> <p><b>Note:</b> Any chemical ingredients listed in Section 15, that do not also appear in Section 2, are contained in the product at a concentration below the applicable OSHA threshold level of 1% or 0.1%.</p>
WHMIS Classification:	B3; D1B; D2B
Regulatory List	Product Ingredients on List
DOT Marine Pollutants (10%)	
DOT Severe Marine Pollutants (1%):	
(No Product Ingredients Listed)	
EPCRA 311/312 Chemicals and RQs (>.1%) :	
(No Product Ingredients Listed)	
EPCRA 302 Extremely Hazardous (>.1%) :	
(No Product Ingredients Listed)	
EPCRA 313 Toxic Chemicals (>.1%) :	
000098-82-8	Cumene
000095-63-6	Pseudocumene
001330-20-7	Xylenes (o-, m-, p- isomers)
Mass RTK Substances (>1%) :	
000095-63-6	Pseudocumene
000108-67-8	TRIMETHYLBENZENE
Mass Extraordinarily Haz Sub (>.01%) :	
(No Product Ingredients Listed)	
Penn RTK Substances (>1%) :	
000095-63-6	Pseudocumene
Penn Special Hazardous Substances (>.01%) :	
(No Product Ingredients Listed)	
Rhode Island Hazardous Substances (>.1%) :	
(No Product Ingredients Listed)	
RCRA Status (>.01%) :	
(No Product Ingredients Listed)	
N.J. RTK Substances (>1%) :	
(No Product Ingredients Listed)	
N.J. Special Hazardous Substances (>.01%) :	
000098-82-8	Cumene
001330-20-7	Xylenes (o-, m-, p- isomers)
N.J. Env. Hazardous Substances (>.1%) :	
000098-82-8	Cumene
000095-63-6	Pseudocumene
001330-20-7	Xylenes (o-, m-, p- isomers)
Proposition 65 – Carcinogens (>0%):	
(No Product Ingredients Listed)	
Proposition 65 – Female Repro Toxins (>0%):	
(No Product Ingredients Listed)	

Proposition 65 – Male Repro  
Toxins (>0%):  
(No Product Ingredients  
Listed)  
Proposition 65 – Developmental  
Toxins (>0%):  
(No Product Ingredients  
Listed)

---

16. OTHER INFORMATION

---

The information and recommendations contained herein are based upon data believed to be correct. However, no guarantee or warranty of any kind, expressed or implied, is made with respect to the information contained herein. We accept no responsibility and disclaim all liability for any harmful effects which may be caused by exposure to our products. Customers/users of this product must comply with all applicable health and safety laws, regulations, and orders.

---

End Of Document